4,4'-Diaminodicyclohexylmethane (PACM, H12MDA)

4,4'-Diaminodicyclohexylmethane (PACM, H12MDA), trans,trans isomer 17 – 24 % · RS-PACM · CAS 1761-71-3 · Technical Data Sheet · RawSource · rawsource.com/product/44-diaminodicyclohexylmethane/

CAS NO.	PRODUCT CODE	PRODUCT TYPE
1761-71-3	RS-PACM	Cycloaliphatic diamine · epoxy curing agent

4,4'-Diaminodicyclohexylmethane (PACM) is mostly used to synthesize transparent aliphatic isocyanate and polyamide resin. It can also be used as an epoxy resin curing agent. It is supplied as a colorless to light yellow liquid. The trans-trans isomer content is 17 – 24 %.

DISTRIBUTED BY
RawSource Inc.
515 E Las Olas Blvd, Suite 1301, Fort Lauderdale, FL 33301
305-307-6515 · solutions@rawsource.com · rawsource.com
Product page: rawsource.com/product/44-diaminodicyclohexylmethane/
Request a quote: solutions@rawsource.com · 305-307-6515
Quote by RS code: RS-PACM

GENERAL INFORMATION

Chemical name	4,4'-Diaminodicyclohexylmethane
Molecular formula	$C_{13}H_{26}N_2$

TYPICAL PROPERTIES

AHEW	52.5

Typical values are representative of the product and are not specifications.

RELEASE SPECIFICATION

PARAMETER	SPECIFICATION
Isomer Rate, trans-trans (%)	17 – 24
Appearance	Colorless to light yellow liquid
Color (APHA)	30 max
Primary amine (wt %)	99.0 min
Viscosity (mPa·s,25 °C)	50 – 80
Moisture (wt %)	0.20 max
Amine Value (mg KOH/g)	500 – 550

Each lot is released against this specification. Lot-specific results are reported on the Certificate of Analysis that ships with every delivery.

KEY FEATURES

- Provides a long pot life in use
- Contributes to high temperature resistance in application
- Contributes to good moisture and chemical resistance in application
- Benefits adhesion on metal substrates
- Allows good color stability

APPLICATIONS

- Synthesis of transparent aliphatic isocyanate and polyamide resin
- Epoxy resin curing agent

Applications are those stated for the product. Confirm suitability for each formulation by trials.

HANDLING REQUIREMENTS

- May be stored under air at ambient temperatures for extended periods.
- A nitrogen blanket is suggested for all storage, to reduce the effect of accidental exposure to high temperatures and to reduce absorption of atmospheric moisture and carbon dioxide.
- Discoloration can occur at temperatures above 60 °C.

PACKAGING AND SHELF LIFE

- 190 kg steel drums
- 950 kg IBC
- bulk
- Shelf life: 12 months from production date.

The information in this Technical Data Sheet is provided for technical evaluation and is believed to be accurate as of the issue date. Typical values are representative and do not constitute a warranty. Binding specifications are those stated on the lot-specific Certificate of Analysis and in the sales contract. Users should verify suitability for their own process and regulatory requirements. Refer to the Safety Data Sheet before handling. Questions: solutions@rawsource.com.