

Polyetheramine D-230

Polyetheramine D-230

PRODUCT CODE	CAS NO.	ISSUED
RS-D230	9046-10-0	July 2026

§1 PRODUCT DESCRIPTION

A difunctional primary polyetheramine (~230 MW) used as an epoxy curing agent and intermediate.

§2 TYPICAL PROPERTIES

PROPERTY	SPECIFICATION	TYPICAL VALUE
Color (APHA)	25 max APHA	—
Primary amine	95.0 min wt %	—
Moisture	0.25 max wt %	—
Amine Value	—	8.1–8.7 meq/g
Viscosity	9.5 cSt/25 °C	9–10
Specific Gravity	25 °C, g/cm ³	0.95
Refractive index	—	1.447 nD ₂₀
Amine hydrogen equivalent	—	60 g/eq (AHEW)

PACKAGING

Standard industrial packaging; drum, IBC, or bulk options quoted per order.

DOCUMENTATION

Full SDS available on request. Lot-specific CoA ships with every order.

Values shown are typical of recent production and do not constitute a sales specification; the lot-specific Certificate of Analysis governs for any shipment. Product is supplied for industrial use only.

Typical batch values, provided in good faith. Contact solutions@rawsource.com for batch-specific data.